



PW Laboratories, Inc.
 6544 Fremont Road - East Syracuse, New York 13057
 Office 315.437.1420 ~ Fax 315.503-3058 ~ pwlabsinc@hotmail.com

Sieve Analysis of Soil / Aggregate

Project Title: Laboratory Testing

Project #: L-22019
 Test Method: ASTM C117 & C136

Report #: 6
 Report Date: August 3, 2022

Source: T.H. Kinsella, Inc. - Fayetteville, NY		Sieve Size - Percent Passing Sieve														
Lab I.D. #	Sample I.D.	3"	2"	1 1/2"	1"	3/4"	1/2"	3/8"	1/4"	#4	#8	#30	#40	#60	#100	#200
42992	Type 1 Crushed Limestone	100	100	91.1	81.3	69.0	49.2	41.1	30.1	24.3	16.0	11.6	10.9	10.0	9.4	8.7
	NYSDOT Specifications Item #733-04A Type 1	100	90-100	-	-	-	-	-	30-65	-	-	-	5-40	-	-	0-10

Sample mass, as received, meets minimum mass requirements of test method: Yes X No _____

Prewashed

Performed By: Mark Santorelli Checked By: Patrick Edmiston

Entire Sample X

Remarks: _____

Mass Retained on #200 Only _____

Not Prewashed: _____