



PW Laboratories, Inc.
 6544 Fremont Road - East Syracuse, New York 13057
 Office 315.437.1420 ~ Fax 315.503-3058 ~ pwlabsinc@hotmail.com

Sieve Analysis of Soil / Aggregate

Project Title: Laboratory Testing

Project #: L-22019
 Test Method: ASTM D422 & D1140

Report #: 3
 Report Date: August 3, 2022

Source: T.H. Kinsella, Inc. - Warlock Quarry		Sieve Size - Percent Passing Sieve														
Lab I.D. #	Sample I.D.	1 1/2"	1"	3/4"	1/2"	3/8"	1/4"	#4	#10	#30	#40	#60	#100	#200		
42989	#1 & #2 Stone Blend	100	97.8	78.7	31.8	15.7	1.9	0.9	0.7	0.7	0.7	0.7	0.7	0.7		

Sample mass, as received, meets minimum mass requirements of test method: Yes X No _____

Prewashed

Performed By: Mark Santorelli Checked By: Patrick Edmiston

Entire Sample X

Remarks: _____

Mass Retained on #200 Only _____

Not Prewashed: _____