



PW Laboratories, Inc.
 6544 Fremont Road - East Syracuse, New York 13057
 Office 315.437.1420 ~ Fax 315.503-3058 ~ pwlabsinc@hotmail.com

Sieve Analysis of Soil / Aggregate

Project Title: Laboratory Testing

Project #: L-22019
 Test Method: ASTM C117 & C136

Report #: 1
 Report Date: August 3, 2022

Source: T.H. Kinsella, Inc. - Warlock Quarry		Sieve Size - Percent Passing Sieve														
Lab I.D. #	Sample I.D.	1 1/2"	1"	3/4"	1/2"	3/8"	1/4"	#4	#8	#30	#40	#60	#100	#200		
42987	#2 Stone	100	99.0	52.5	6.1	1.4	0.8	0.8	0.8	0.8	0.8	0.8	0.7	0.8		
	NYS DOT Specifications Item #703-4 #2 Size	100	90-100	-	0-15	-	-	-	-	-	-	-	-	0-1.0 (1)		

(1) The minus 200 material requirements apply only to aggregate for use in Portland cement concrete surface treatments and cold mix bituminous pavements. The test (NYS DOT 201) will be performed on the entire sample of the designated size aggregate. Primary size does not apply in the determination of the minus #200 material.

Sample mass, as received, meets minimum mass requirements of test method: Yes X No _____

Performed By: Mark Santorelli Checked By: Patrick Edmiston

Remarks: _____

Prewashed
 Entire Sample X
 Mass Retained on #200 Only _____
 Not Prewashed: _____