



PW Laboratories, Inc.

6544 Fremont Road - East Syracuse, New York 13057

Office 315.437.1420 ~ Fax 315.503-3058 ~ pwlabsinc@hotmail.com

Sieve Analysis of Soil / Aggregate

Project Title: Laboratory Testing

Project #: L-22019

Test Method: ASTM C117 & C136

Report #: 7

Report Date: June 7, 2022

Source: T.H. Kinsella, Inc. - Fayetteville, NY		Sieve Size - Percent Passing Sieve														
Lab I.D. #	Sample I.D.	2"	1 1/2"	1"	3/4"	1/2"	3/8"	1/4"	#4	#10	#30	#40	#60	#100	#200	
42662	Type 2 Crushed Limestone	100	100	98.7	85.6	65.5	56.0	40.7	33.7	20.3	12.3	10.6	9.5	8.9	7.8	
	NYSDOT Specifications Item #703-4 Type 2	100	-	-	-	-	-	25-60	-	-	-	5-40	-	-	0-10	

Sample mass, as received, meets minimum mass requirements of test method: Yes X No _____

Prewashed

Performed By: Mark Santorelli Checked By: Patrick Edmiston

Entire Sample X

Remarks: _____

Mass Retained on #200 Only _____

Remarks: _____

Not Prewashed: _____