



PW Laboratories, Inc.

6544 Fremont Road - East Syracuse, New York 13057

Office 315.437.1420 ~ Fax 315.503-3058 ~ pwlabsinc@hotmail.com

Sieve Analysis of Soil / Aggregate

Project Title: Laboratory Testing

Project #: L-22019

Test Method: ASTM D422 & D1140

Report #: 5

Report Date: June 7, 2022

Source: T.H. Kinsella, Inc. - Fayetteville, NY		Sieve Size - Percent Passing Sieve														
Lab I.D. #	Sample I.D.	1 1/2"	1"	3/4"	1/2"	3/8"	1/4"	#4	#10	#30	#40	#60	#100	#200		
42660	S1 & #2 Stone Blend	100	99.4	84.8	48.4	28.0	1.0	0.3	0.2	0.2	0.1	0.1	0.1	0.1		

Sample mass, as received, meets minimum mass requirements of test method: Yes X No _____

Prewashed

Performed By: Mark Santorelli Checked By: Patrick Edmiston

Entire Sample X

Remarks: _____

Mass Retained on #200 Only _____

Not Prewashed: _____